

TECHNI-CAST	814	624	1020	555
FEDERAL	QQ-C-390A, CA 923	QQ-C-390A, CA 922		QQ-C-390A, CA 836
	QQ-C-390, D3	QQ-C-390, D4		QQ-C-390, B5
	QQ-B-1005, Comp. 10	QQ-B-1005, Comp. 1		QQ-B-1005, Comp. 2
MILITARY	MIL-C-15345g, #10	MIL-C-15345g, #9		MIL-C-15345g, #1
	MIL-C-15345A, #4	MIL-C-15345A, #2		MIL-C-15345A, #1
		MIL-B-16541B		MIL-B-16444A, Gr. A
NAVY	46B5j, Gr. I & II	46B8i, Gr. I		46B23e, Gr. A
		45F12		45B5d, Gr. B
ASTM	B-143, CA 923	B-143, CA 922		B-145, CA 836
	B-143, 2B	B-143, 2A		B-145, 4A
	B-271, C92300	B-271, C92200		B-62
	B-584, C92300	B-584, C92200		B-584, C83600
		B-61		B-271, C83600
SAE	C92300	C92200	C92700	C86300
	621	622	63	40
				-791
AMS				4855B
COPPER	87.25	88.50	88.00	85.00
TIN	8.00	6.00	10.00	5.00
LEAD	0.75	1.50	2.00	5.00
ZINC	4.00	4.00		5.00
TENSILE STRENGTH, psi	40,000	40,000	42,000	35,000
YIELD STRENGTH, psi	20,000	18,000	23,000	20,000
ELONGATION, %	25	30	18	25