

TECHNI-CAST	CN7030	CN9010
FEDERAL	QQ-C-390A, CA 964	QQ-C-390A, CA 962
	QQ-C-390, X9	
MILITARY	MIL-C-15345g, #24	MIL-C-15345g, #25
	MIL-C-20159B, TY. I	MIL-C-20159B, TY. II
NAVY	46C8a, Gr. I	
ASTM	B-369, CA 964	B-369, CA 962
	B-369, B	B-369, A
SAE	C96400	C96200
AMS		
COPPER	67.00	87.00
ZINC		
IRON	0.75	1.25
SILICON	0.35	0.20
NICKEL	30.00	10.00
COBALT		
MANGANESE	0.75	0.75
BERYLLIUM		
NIObIUM	1.15	0.80
CHROMIUM		
TENSILE STRENGTH, psi	72,000	50,000
YIELD STRENGTH, psi	40,000	30,000
ELONGATION %	35	28
HARDNESS, BRINELL	135	
CONDITION	AC	AC